

ABOUT FLY TYING THREAD

By Christopher Helms (Source – 2006 Whitetail Catalogue)

For my personal tying I use primarily Gudebrod, Benecchi, and ULTRA thread, along with Gudebrod GX 2 or Dynacord for deer hair work. These threads provide the right strength size and appropriate attributes such as the ability to flatten that I find makes tying durable and beautiful flies much easier.

USING DENIER TO STANDARDIZE FLY TYING THREAD

In the summer 2004 issue of Fly Tyer, author Lyle Morgan addressed the question of whether standardizing thread size would help tiers become more effective in producing beautiful and effective flies. It certainly makes sense to have standardization, which would eliminate much of the confusion that surrounds fly tying thread today. Based on the fly tier web poll conducted in the same issue as Lyle's article, voters overwhelmingly agreed (252 to 32) that thread should be standardized. The process has begun and over the next few years you will begin to see the denier (pronounced DEN yer) number listed on most of the spools of the major thread distributors.

Tom Schmuecker of WAPSI started the denier information process by introducing WAPSI UTC 70 and 140 denier threads in 1998. His purpose in using the denier number rather than the "aught" was to try and subtly suggest that this system was more beneficial to the tier than the "aught" system that had existed for more than seventy years. Denier is also a recognized and accepted standard of measurement among thread manufacturers and the garment industry.

Jean Guy Cote' of UNI Products is already putting the denier on a number of his products. He stated, however, " I won't put the denier on the 8/0 thread until I am sure that all of the other distributors are using the same measurement system to identify the denier of their thread". Those discussions are currently taking place and I am confident that he will eventually put the denier on the 8/0 spools. He has already identified in a chart the denier of all of his products. This information is available to anyone requesting it

Paul Black of Gudebrod stated, " I have already started to put the denier number on the labels of our thread since we do all of our printing in house" Of course, this process may take a year or more to complete given the number of thread sizes (7) and the multitude of colors. These new labels will begin to show up in fly shops gradually as the proprietors order new stock.

Danville manager, Dan Bezanson, stated, "Wherever possible, Danville will include the denier on the spool label." A few labels may not contain the denier due to unavailable space. Danville recently introduced a 140 denier thread that does not have an "aught" designation.

Giorgio Benecchi Products, of Modena, Italy, does not have labels on their spools. However, they do provide this information freely to shops or distributors. In my own

shop, I use a rubber stamp to put the denier as well as the "aught" rating on each spool of Benecchi thread.

Historically the "aught" system began in the late 1930's. Dan Bezanson said, " Based on the information that has been handed down in the company, Danville Chenille implemented the "aught" system to help standardize fly tying thread. This was based on a system where the number 0 or "aught" was the base point and as the thread became smaller additional zeros were added indicating that the thread was finer. As an example, a thread with six zeros (000000) translated to a 6/0 thread. As other thread distributors came into the market place after the early 1960's, they followed the same system which was assigning a standard that does not necessarily provide as accurate a measurement for the fly tier as denier

As more thread distributors and brands became available, the accuracy of the "aught" became muddled. When only one distributor existed, making some sense of the system was not difficult. Now there are at least seven distributors of thread in what has become a very competitive market. It occurred to me in the mid 1990's that some of the aught numbers being assigned to some thread was a matter of trying to gain a competitive edge rather than providing accuracy for the fly tying customer. That is precisely what generated the article I coauthored with Bill Merg in the summer 1996 issue of Fly Tyeer entitled "Testing the Ties That Bind". The focus of this article was on a number of aspects of thread but emphasized breaking strength and thickness.

Denier is defined as the weight in grams of 9000 meters of nylon, polyester, rayon thread, etc. There is a correlation between denier and breaking strength of nylon and polyester thread. The smaller the denier numbers the lower pound / ounce breaking strength of the thread. At the present time, about the smallest denier nylon or polyester for fly tying thread is 40, which would be used for tying midges. The one exception to this denier vs. breaking strength rule is that gel spun polyethylene thread is two to three times stronger than nylon or polyester thread of the same denier.

Denier is only one factor the tier should take into consideration when selecting a thread. The type of material of which the thread is constructed should be considered, whether the thread is a continuous filament, simple twist, bonded, or a rope type. Nylon has about 25% stretch, polyester around 15% stretch, and gel spun only 3% stretch. The type of material being used on the fly as well as the appearance desired also has to be considered. It is important to experiment with all of the various threads available to gain a complete understanding of the pros and cons of each. Listed below are some of the most popular brands and sizes of threads available. Compare the denier of the thread you are using with others of a similar "aught" size.

Bill Merg conducted the tests on 15 threads that have become available in the past several years. All of the other data listed in the chart is from the 1996 test results. He used the same methodology in testing the various new threads that have become available in the past few years as the tests conducted for the thread listed in the 1996 article entitled "Testing the Ties That Bind", that is mentioned above. On all of the tests

conducted in 1995, the various brands showed remarkable consistency in thickness throughout the spool. That was not the case in a number of the threads recently entering the marketplace. Those that showed slight variation in thickness included: (variation shown) WAPSI 210 (.008), WAPSI 280 (005), and Danville 140 (006), Roman Moser Power Silk 6/0 (0012). Keep in mind that one spool was randomly selected and used for these tests.

Another thread article by Ed Engle in the spring 2000 issue of *Fly Tyer* entitled "Hanging by a Thread" compares twelve different threads for tying small flies. Then he rates the threads in a manner similar to how *Consumer Reports* evaluates products. This same article appears in Ed's book *Tying Small Flies*. Ed describes the qualities of twelve threads and discusses the characteristics of each.

Darrel Martin wrote an excellent article on thread in the March/April 2000 of *Fly Rod and Reel* entitled "A Thread of An Idea". He discusses silk thread and its history along with numerous facts about thread sizing, characteristics of the each material used in thread. He also comments on thread pressure applied when tying and characteristics of waxed thread. Matching the thread to the size of the fly and the material being used is extremely important in achieving both functional and aesthetically pleasing flies. The more a tier understands about all the materials used in tying the fly the more efficient and effective fly tier he or she will become.

TABLE SORTED BY DENIER:

Thread Brand	Aught Size	Material	Denier	Breaking Strength	Breaking Strength (oz)	Thickness (.000)
UNI Caenis	N/A	mono	20	3 oz	3	1.7
Danville Spiderweb	N/A	mono	30	5 oz	5	2.0
UNI Trico	17/0	nylon	40	5 oz	5	2.0
Gudebrod	10/0	polyester	45	9 oz	9	1.0
WAPSI 50 GSP	N/A	gel spun	50	2 lbs. 5 oz	37	0.8
UNI Cord	12/0	gel spun	50	2 lbs. 7 oz	39	0.9
Benecchi Ultra Strong	N/A	gel spun	50	2 lbs. 6 oz	38	1.3
Gudebrod	10/0	mono	50	2 lbs. 11 oz	43	6.0
Roman Moser Power Silk	8/0	gel spun	55	2 lbs. 6 oz	38	1.3
Benecchi Ghost	N/A	mono	60	11 oz	11	3.0
Gudebrod	8/0	polyester	67	15 oz	15	1.8
Benecchi	12/0	polyester	70	15 oz	15	1.9
Gudebrod GXI	N/A	gel spun	70	7 lbs. 1 oz	113	1.1
Danville	6/0	nylon	70	11 oz	11	1.5
WAPSI UTC 70	N/A	nylon	70	13 oz	13	1.1
Gordon Griffith Shear	14/0	polyester	72	10 oz	10	1.8
UNI	8/0	polyester	72	15 oz	15	2.0
UNI Cord	7/0	gel spun	100	5 lbs. 9 oz	89	1.4
WAPSI GSP 100	N/A	gel spun	100	6 lbs. 15 oz	111	1.2
Gordon Griffith Wisp	8/0	polyester	108	15 oz	15	2.2
Roman Moser Power Silk	6/0	gel spun	110	4 lbs. 8 oz.	72	1.3
Danville Monocord	3/0	nylon	116	1 lb. 10 oz	26	2.6
Benecchi	10/0	polyester	120	1 lb. 6 oz	22	2.0
Gudebrod GX2	N/A	gel spun	130	6 lbs. 8 oz	104	2.0
Gordon Griffith Cobweb 2	N/A	polyester	134	4 lbs. 3 oz	67	4.1
UNI	6/0	nylon	135	1 lb. 13 oz	29	2.9
WAPSI UTC 140	N/A	nylon	140	2 lbs. 12 oz	44	1.6
Gudebrod	6/0	polyester	143	1 lb. 15 oz	31	2.3
Gudebrod	6/0	mono	143	2 lbs. 11 oz	43	6.0
Benecchi	8/0	polyester	150	1 lb. 13 oz	29	2.2
Gudebrod	3/0	polyester	176	2 lbs. 6 oz	38	4.0
Danville Flat Waxed Nylon	N/A	nylon	210	2 lbs. 14 oz	46	2.0
Danville Fly Master Plus	N/A	nylon	210	3 lbs	36	2.8
UNI 210	N/A	nylon	210	3 lbs. 3 oz	51	2.0
WAPSI UTC 210	N/A	nylon	210	3 lbs. 5 oz	53	3.2
Gudebrod G	N/A	mono	210	3 lbs. 7 oz	55	7.0
WAPSI UTC 280	N/A	nylon	280	3 lbs 14 oz	62	2.7
Gudebrod G	N/A	polyester	330	3 lbs. 11 oz	59	3.5
UNI Big Fly Thread	N/A	nylon	440	5 lbs. 4 oz	84	3.5

TABLE SORTED BY THICKNESS:

Thread Brand	Aught Size	Material	Denier	Breaking Strength	Breaking Strength (oz)	Thickness (.000)
WAPSI 50 GSP	N/A	gel spun	50	2 lbs. 5 oz	37	0.8
UNI Cord	12/0	gel spun	50	2 lbs. 7 oz	39	0.9
Gudebrod	10/0	polyester	45	9 oz	9	1.0
Gudebrod GXI	N/A	gel spun	70	7 lbs. 1 oz	113	1.1
WAPSI UTC 70	N/A	nylon	70	13 oz	13	1.1
WAPSI GSP 100	N/A	gel spun	100	6 lbs. 15 oz	111	1.2
Benecci Ultra Strong	N/A	gel spun	50	2 lbs. 6 oz	38	1.3
Roman Moser Power Silk	8/0	gel spun	55	2 lbs. 6 oz	38	1.3
Roman Moser Power Silk	6/0	gel spun	110	4 lbs. 8 oz.	72	1.3
UNI Cord	7/0	gel spun	100	5 lbs. 9 oz	89	1.4
Danville	6/0	nylon	70	11 oz	11	1.5
WAPSI UTC 140	N/A	nylon	140	2 lbs. 12 oz	44	1.6
UNI Caenis	N/A	mono	20	3 oz	3	1.7
Gudebrod	8/0	polyester	67	15 oz	15	1.8
Gordon Griffith Shear	14/0	polyester	72	10 oz	10	1.8
Benecci	12/0	polyester	70	15 oz	15	1.9
Danville Spiderweb	N/A	mono	30	5 oz	5	2.0
UNI Trico	17/0	nylon	40	5 oz	5	2.0
UNI	8/0	polyester	72	15 oz	15	2.0
Benecci	10/0	polyester	120	1 lb. 6 oz	22	2.0
Gudebrod GX2	N/A	gel spun	130	6 lbs. 8 oz	104	2.0
Danville Flat Waxed Nylon	N/A	nylon	210	2 lbs. 14 oz	46	2.0
UNI 210	N/A	nylon	210	3 lbs. 3 oz	51	2.0
Gordon Griffith Wisp	8/0	polyester	108	15 oz	15	2.2
Benecci	8/0	polyester	150	1 lb. 13 oz	29	2.2
Gudebrod	6/0	polyester	143	1 lb. 15 oz	31	2.3
Danville Monocord	3/0	nylon	116	1 lb. 10 oz	26	2.6
WAPSI UTC 280	N/A	nylon	280	3 lbs 14 oz	62	2.7
Danville Fly Master Plus	N/A	nylon	210	3 lbs	36	2.8
UNI	6/0	nylon	135	1 lb. 13 oz	29	2.9
Benecci Ghost	N/A	mono	60	11 oz	11	3.0
WAPSI UTC 210	N/A	nylon	210	3 lbs. 5 oz	53	3.2
Gudebrod G	N/A	polyester	330	3 lbs. 11 oz	59	3.5
UNI Big Fly Thread	N/A	nylon	440	5 lbs. 4 oz	84	3.5
Gudebrod	3/0	polyester	176	2 lbs. 6 oz	38	4.0
Gordon Griffith Cobweb 2	N/A	polyester	134	4 lbs. 3 oz	67	4.1
Gudebrod	10/0	mono	50	2 lbs. 11 oz	43	6.0
Gudebrod	6/0	mono	143	2 lbs. 11 oz	43	6.0
Gudebrod G	N/A	mono	210	3 lbs. 7 oz	55	7.0

TABLE SORTED BY BREAKING STRENGTH:

Thread Brand	Aught Size	Material	Denier	Breaking Strength	Breaking Strength (oz)	Thickness (.000)
UNI Caenis	N/A	mono	20	3 oz	3	1.7
Danville Spiderweb	N/A	mono	30	5 oz	5	2.0
UNI Trico	17/0	nylon	40	5 oz	5	2.0
Gudebrod	10/0	polyester	45	9 oz	9	1.0
Gordon Griffith Shear	14/0	polyester	72	10 oz	10	1.8
Benecchi Ghost	N/A	mono	60	11 oz	11	3.0
Danville	6/0	nylon	70	11 oz	11	1.5
WAPSI UTC 70	N/A	nylon	70	13 oz	13	1.1
Gudebrod	8/0	polyester	67	15 oz	15	1.8
Benecchi	12/0	polyester	70	15 oz	15	1.9
UNI	8/0	polyester	72	15 oz	15	2.0
Gordon Griffith Wisp	8/0	polyester	108	15 oz	15	2.2
Benecchi	10/0	polyester	120	1 lb. 6 oz	22	2.0
Danville Monocord	3/0	nylon	116	1 lb. 10 oz	26	2.6
UNI	6/0	nylon	135	1 lb. 13 oz	29	2.9
Benecchi	8/0	polyester	150	1 lb. 13 oz	29	2.2
Gudebrod	6/0	polyester	143	1 lb. 15 oz	31	2.3
Danville Fly Master Plus	N/A	nylon	210	3 lbs	36	2.8
WAPSI 50 GSP	N/A	gel spun	50	2 lbs. 5 oz	37	0.8
Benecchi Ultra Strong	N/A	gel spun	50	2 lbs. 6 oz	38	1.3
Roman Moser Power Silk	8/0	gel spun	55	2 lbs. 6 oz	38	1.3
Gudebrod	3/0	polyester	176	2 lbs. 6 oz	38	4.0
UNI Cord	12/0	gel spun	50	2 lbs. 7 oz	39	0.9
Gudebrod	10/0	mono	50	2 lbs. 11 oz	43	6.0
Gudebrod	6/0	mono	143	2 lbs. 11 oz	43	6.0
WAPSI UTC 140	N/A	nylon	140	2 lbs. 12 oz	44	1.6
Danville Flat Waxed Nylon	N/A	nylon	210	2 lbs. 14 oz	46	2.0
UNI 210	N/A	nylon	210	3 lbs. 3 oz	51	2.0
WAPSI UTC 210	N/A	nylon	210	3 lbs. 5 oz	53	3.2
Gudebrod G	N/A	mono	210	3 lbs. 7 oz	55	7.0
Gudebrod G	N/A	polyester	330	3 lbs. 11 oz	59	3.5
WAPSI UTC 280	N/A	nylon	280	3 lbs 14 oz	62	2.7
Gordon Griffith Cobweb 2	N/A	polyester	134	4 lbs. 3 oz	67	4.1
Roman Moser Power Silk	6/0	gel spun	110	4 lbs. 8 oz.	72	1.3
UNI Big Fly Thread	N/A	nylon	440	5 lbs. 4 oz	84	3.5
UNI Cord	7/0	gel spun	100	5 lbs. 9 oz	89	1.4
Gudebrod GX2	N/A	gel spun	130	6 lbs. 8 oz	104	2.0
WAPSI GSP 100	N/A	gel spun	100	6 lbs. 15 oz	111	1.2
Gudebrod GXI	N/A	gel spun	70	7 lbs. 1 oz	113	1.1

TABLE SORTED BY BRAND THEN BY STRENGTH:

Thread Brand	Aught Size	Material	Denier	Breaking Strength	Breaking Strength (oz)	Thickness (.000)
Benecchi	12/0	polyester	70	15 oz	15	1.9
Benecchi	10/0	polyester	120	1 lb. 6 oz	22	2.0
Benecchi	8/0	polyester	150	1 lb. 13 oz	29	2.2
Benecchi Ghost	N/A	mono	60	11 oz	11	3.0
Benecchi Ultra Strong	N/A	gel spun	50	2 lbs. 6 oz	38	1.3
Danville	6/0	nylon	70	11 oz	11	1.5
Danville Flat Waxed Nylon	N/A	nylon	210	2 lbs. 14 oz	46	2.0
Danville Fly Master Plus	N/A	nylon	210	3 lbs	36	2.8
Danville Monocord	3/0	nylon	116	1 lb. 10 oz	26	2.6
Danville Spiderweb	N/A	mono	30	5 oz	5	2.0
Gordon Griffith Cobweb 2	N/A	polyester	134	4 lbs. 3 oz	67	4.1
Gordon Griffith Shear	14/0	polyester	72	10 oz	10	1.8
Gordon Griffith Wisp	8/0	polyester	108	15 oz	15	2.2
Gudebrod	10/0	polyester	45	9 oz	9	1.0
Gudebrod	8/0	polyester	67	15 oz	15	1.8
Gudebrod	6/0	polyester	143	1 lb. 15 oz	31	2.3
Gudebrod	3/0	polyester	176	2 lbs. 6 oz	38	4.0
Gudebrod	10/0	mono	50	2 lbs. 11 oz	43	6.0
Gudebrod	6/0	mono	143	2 lbs. 11 oz	43	6.0
Gudebrod G	N/A	mono	210	3 lbs. 7 oz	55	7.0
Gudebrod G	N/A	polyester	330	3 lbs. 11 oz	59	3.5
Gudebrod GX2	N/A	gel spun	130	6 lbs. 8 oz	104	2.0
Gudebrod GXI	N/A	gel spun	70	7 lbs. 1 oz	113	1.1
Roman Moser Power Silk	8/0	gel spun	55	2 lbs. 6 oz	38	1.3
Roman Moser Power Silk	6/0	gel spun	110	4 lbs. 8 oz.	72	1.3
UNI	8/0	polyester	72	15 oz	15	2.0
UNI	6/0	nylon	135	1 lb. 13 oz	29	2.9
UNI 210	N/A	nylon	210	3 lbs. 3 oz	51	2.0
UNI Big Fly Thread	N/A	nylon	440	5 lbs. 4 oz	84	3.5
UNI Caenis	N/A	mono	20	3 oz	3	1.7
UNI Cord	12/0	gel spun	50	2 lbs. 7 oz	39	0.9
UNI Cord	7/0	gel spun	100	5 lbs. 9 oz	89	1.4
UNI Trico	17/0	nylon	40	5 oz	5	2.0
WAPSI 50 GSP	N/A	gel spun	50	2 lbs. 5 oz	37	0.8
WAPSI GSP 100	N/A	gel spun	100	6 lbs. 15 oz	111	1.2
WAPSI UTC 140	N/A	nylon	140	2 lbs. 12 oz	44	1.6
WAPSI UTC 210	N/A	nylon	210	3 lbs. 5 oz	53	3.2
WAPSI UTC 280	N/A	nylon	280	3 lbs 14 oz	62	2.7
WAPSI UTC 70	N/A	nylon	70	13 oz	13	1.1